

Special Provision to Special Specification 6019

Longitudinal Prefabricated Pavement Markings (PPM) with Warranty



For this project, Special Specification “Longitudinal Prefabricated Pavement Markings (PPM) with Warranty,” is hereby amended with respect to the clauses cited below, and no other clauses or requirements of this Item are waived or changed hereby.

Section 5.2., Retroreflectivity, is voided and replaced by the following:

5.2. Dry Retroreflectivity. Provide PPM meeting the minimum Retroreflectivity values listed in Table 2.

Table 2
Minimum Retroreflectivity Requirements

Color	Retroreflectivity, mcd/m ² /tx, Min
White	120
Yellow	120

Wet Reflectivity, required for this contract, pavement markings, both white and yellow, will maintain a minimum coefficient of retroreflected luminance of 75 millicandelas/square meter/lux when measured at “30 meter” geometry under a “condition of wetness” in accordance with ASTM E 2177.

Section 5.4. Performance Evaluation Process is supplemented by the following:

5.4.1. Adhesion. Pavement markings will remain in the proper alignment and location. Deviations in alignment or location caused by, in the Engineer’s opinion, pavement failure will not be considered as a failure of the pavement markings.

Article 6. Warranty Requirements is supplemented by the following:

Wet Reflectivity Life, as required by this contract, longitudinal markings, and symbols, and legends will meet wet reflectivity performance requirements described in Section 5 for 2 years, as measured in accordance with ASTM E 2177.