

# Special Provision to Special Specification 6019

## Longitudinal Prefabricated Pavement Markings (PPM) with Warranty



For this project, Special Specification “Longitudinal Prefabricated Pavement Markings (PPM) with Warranty,” is amended with respect to the clauses cited below, and no other clauses or requirements of this Item are waived or changed.

Section 5.2., “Retroreflectivity,” is voided and replaced by the following:

5.2.1. **Dry Retroreflectivity.** Provide PPM meeting the minimum retroreflectivity values listed in Table 2.

**Table 2**  
**Minimum Retroreflectivity Requirements**

Color	Retroreflectivity, mcd/m <sup>2</sup> /tx, Min
White	120
Yellow	120

5.2.2. **Wet Reflectivity.** Required for this Contract, pavement markings, both white and yellow, will maintain a minimum coefficient of retroreflected luminance of 75 millicandelas/square meter/lux when measured at “30 meter” geometry under a “condition of wetness” in accordance with ASTM E 2177.

Section 5.4., “Performance Evaluation Procedures,” is supplemented by the following:

5.4.4. **Adhesion.** Pavement markings will remain in the proper alignment and location. Deviations in alignment or location which, in the Engineer’s opinion, is caused by pavement failure will not be considered as a failure of the pavement markings.

Article 6., “Warranty Requirements,” is supplemented by the following:

Wet Reflectivity Life, as required by this Contract, longitudinal markings, and symbols, and legends will meet wet reflectivity performance requirements described in Section 5 for 2 yr., as measured in accordance with ASTM E 2177.