

# Special Provision to Special Specification 6159

## All-Weather Paint



Special Specification 6159 "All-Weather Paint," is amended with respect to the clauses cited below. No other clauses or requirements of this Item are waived or changed.

Section 4.3, "Retroreflective Requirements". Table 1 and Table 2 are voided and replaced by the following:

**Table 1**  
Retroreflectivity  
(mcd/ft<sup>2</sup>) {metric equivalent {mcd/lux/m<sup>2</sup>}}

	White	Yellow
Dry	350	275
Wet continuous (ASTM 2832)	100	75

**Table 2**  
Retroreflectivity  
(mcd/ft<sup>2</sup>) {metric equivalent {mcd/lux/m<sup>2</sup>}}

	White	Yellow
Dry	250	200
Wet continuous (ASTM 2832)	75	75