

Special Provision to Special Specification 6159

All-Weather Paint



Special Specification 6159, "All-Weather Paint," is amended with respect to the clauses cited below. No other clauses or requirements of this Item are waived or changed.

Section 4.3., "Retroreflective Requirements." Table 1 and Table 2 are voided and replaced by the following.

Table 1
Retroreflectivity
(mcd/ft²) {metric equivalent (mcd/lux/m²)}

	White	Yellow
Dry	350	275
Wet continuous (ASTM 2832)	100	75

Table 2
Retroreflectivity
(mcd/ft²) {metric equivalent (mcd/lux/m²)}

	White	Yellow
Dry	250	200
Wet continuous (ASTM 2832)	75	75