

# Special Provision to Special Spec 8013

## Hot-Mix Cold-Laid Asphalt Concrete Pavement (Material Only)



Special Spec 8013, "Hot-Mix Cold-Laid Asphalt Concrete Pavement (Material Only)" of the Standard Specifications is amended with respect to the clauses cited below. No other clauses or requirements of this Item are waived or changed hereby.

Section 8013.4.1.2, "Job-Mix Formula Approval," Table 5, is voided and replaced by the following:

**Table 5**  
**Laboratory Mixture Design Properties**

Property	Test Method	Requirement
Target laboratory -molded density, % <sup>1</sup>	<a href="#">Tex-207-F</a>	95 ± 1.0
Hveem stability, Min	<a href="#">Tex-208-F</a>	35
Hydrocarbon-volatile content, %, Max	<a href="#">Tex-213-F</a>	0.6
Moisture content, %, Max <sup>2</sup>	<a href="#">Tex-212-F</a>	1.0
Boil test, %, Max <sup>3</sup>	<a href="#">Tex-530-C</a>	10

1. Unless otherwise shown on the plans.
2. Unless otherwise approved.
3. Limit may be increased or eliminated when approved.