

Special Provision to Item 302

Aggregates for Surface Treatments



Item 302, "Aggregates for Surface Treatment" of the Standard Specifications is amended with respect to the clauses cited below. No other clauses or requirements of this Item are waived or changed.

Section 302.2.1, "Aggregate". Table 2 is supplemented with the following grades:

Table 2
Aggregate Gradation Requirements (Cumulative % Retained¹)

	Grade
	4M
1"	-
7/8"	-
3/4"	-
5/8"	0
1/2"	0 – 15
3/8"	35 – 65
1/4"	-
#4	95 – 100
#8	98 – 100

1.Round test results to the nearest whole number.

Grade 4M will have 98.5% to 100% retained on a No. 200 sieve.