

# Special Provision to Item 334

## Hot-Mix Cold-Laid Asphalt Concrete Pavement



Item 334, "Hot-Mix Cold-Laid Asphalt Concrete Pavement," of the Standard Specifications is amended with respect to the clauses cited below. No other clauses or requirements of this Item are waived or changed hereby.

Section 334.4.1.2., "Job-Mix Formula Approval," Table 5, is voided and replaced by the following:

**Table 5**  
**Laboratory Mixture Design Properties**

| Property   | Test Method               | Requirement |
|--|---------------------------|-------------|
| Target laboratory-molded density, % <sup>1</sup> | <a href="#">Tex-207-F</a> | 94.0 ± 1.5  |
| Hveem stability, Min                             | <a href="#">Tex-208-F</a> | 35          |
| Hydrocarbon-volatile content, %, Max             | <a href="#">Tex-213-F</a> | 0.6         |
| Moisture content, %, Max <sup>2</sup>            | <a href="#">Tex-212-F</a> | 1.0         |
| Boil test, %, Max <sup>3</sup>                   | <a href="#">Tex-530-C</a> | 10          |

1. Unless otherwise shown on the plans.
2. Unless otherwise approved.
3. Limit may be increased or eliminated when approved.