

Special Provision to Item 721

Fiber Reinforced Polymer Patching Material



Item 721, "Fiber Reinforced Polymer Patching Material" of the Standard Specifications is amended with respect to the clauses cited below. No other clauses or requirements of this Item are waived or changed.

Article 3., "Materials," Table 1 is voided and replaced by the following:

Table 1
Patching Material Properties

Property	Test Method	Requirement
Resilience	Tex-547-C	50% Min
Tensile Strain to Failure	Tex-548-C	20% Min
Maximum Tensile Stress	Tex-548-C	50 psi Min
Cone Flow	Tex-549-C	12% Max (asphalt based) 4% Max (polymer based)
Flexibility	Tex-550-C	pass ¹
Settlement	Tex-551-C	3 mm, Max

1. No evidence of cracking of the sample.

Section 3.1., "Sampling and Testing," is voided and replaced by the following:

- 3.1. **Sampling and Testing.** Provide material that has been preapproved by the Department in accordance with [Tex-538-C](#), "Quality Monitoring for Rubber Asphalt Crack Sealers and Related Materials." Submit blended samples of patching material for preapproval or field evaluation when requested.